



DATE : 1 OCT 2015

VERSION NO. : 6

PAGE : 1 OF 1

MPPI

## Product Information Sheet

Mainland Paint & Printing Ink Ltd.  
PO Box 12-171, 351 Selwyn St,  
Christchurch 8242, New Zealand  
Phone : ++ 64 3 338-1312  
Fax : ++ 64 3 338-1522  
Email : sales@mppi.co.nz



Quality  
ISO 9001

# Wood Green & Clear

### INTRODUCTION

Mainland Wood Green / Clear - Timber Preservative

Wood Green ( Copper Naphthenate )

Wood Clear ( Zinc Naphthenate )

Provides extra protection to stop rot and prevent mildew growth. Wood Green should be used wherever possible. Wood Clear should only be used where it is not desired to alter the colour of the article.

### TYPICAL USES

- \* Houses \* Garages \* Fence posts \* Battens \* Trellis work \* Seed boxes
- \* Garden stakes \* Farm buildings \* Outhouses \* Cow and poultry sheds \* Pigsty
- \* Beehives. On all woodwork of Yachts \* Launches \* Plywood craft \* Caravans
- \* Truck and Bus bodies.

### PHYSICAL PROPERTIES

Vehicle Type - Naphthenic Acid

Pigmentation - Nil

Solvent - Mineral Turps

Pot Life - Not applicable

Finish - Matt

Colour - Green / Clear

Dry Time - 48 Hours minimum

Re-coat - 4 weeks if necessary

Primer Required - No

Theoretical coverage - 8 to 10 sq. metres/litre

Dry Film Thickness - Penetrating Type

Usual No. of coats - One liberally applied

Heat Resistance - Fair

Chemical Resistance - Fair

Abrasion Resistance - Poor

Solvent Resistance - Fair

Thinning & Clean up - Mineral Turpentine

Can Sizes - 20 lt., 4 lt., 1 lt. & 500 ml

### PERFORMANCE AND LIMITATIONS

Performance

- (1) Has excellent penetration and wood preserving qualities
- (2) Suitable for both dressed and rough sawn timber.
- (3) Easily recoated with minimum surface preparation.
- (4) When dry will not affect young plants or bees (insects).
- (5) When diluted with used lubricating oil is an economical preservative for soft woods on farm buildings not subsequently to be painted.

Limitations

- (1) In areas where maximum exposure of the timber, more frequent applications may be required.
- (2) Mainland Wood Green / Clear is a penetrating material and care should be taken on hard impervious timbers, dilution with Mineral Turpentine may be necessary to assist penetration.